

TEST REPORT

APPLICANT : Taizhou Huangyan Pengxin Plastic Machine Co., Ltd

ADDRESS : NO.8 YaLin Industrial Park Huang Yan Tai Zhou

SAMPLE DESCRIPTION : PET Blue Bottle Body, PE Blue Lid, PE Blue Nozzle

SAMPLE RECEIVED DATE : 06-Nov-2013

TURN AROUND TIME : 06-Nov-2013 to 11-Nov-2013, 4 working days

TEST REQUESTED : Selected test(s) as requested by client

TEST METHOD : Please refer to next page(s)

TEST RESULT : Please refer to next page(s)

Eurofins (Shanghai) contact informationCustomer service: LillianLi@eurofins.com / 021-61819105 / 13816539083Sales specialist: MichaelXu@eurofins.com /021-61819165/13524163600

***** FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) *****

Signed for and on behalf of
Eurofins Product Testing Service (Shanghai) Co., Ltd



Chris Zhang
Lab Manager

SAMPLE PHOTO



EFSH13110287-ST

TO BE CONTINUED

TEST RESULT

<u>Sample No.</u>	<u>Sample Description</u>	<u>Test Item(s)</u>	<u>Test Result</u>	<u>Unit</u>	<u>Test Method</u>
072013014427	PET Blue body	evaporation residue (water)	<5.0	mg/L	GB/T 5009.60-2003 GB/T 5009.156-2003
072013014427	PET Blue body	evaporation residue (4% acetic acid)	<5.0	mg/L	
072013014427	PET Blue body	evaporation residue (65% ethanol)	<5.0	mg/L	
072013014427	PET Blue body	evaporation residue (Hexane)	15.2	mg/L	
072013014427	PET Blue body	potassium permanganate consumption	0.525	mg/L	
072013014427	PET Blue body	Heavy metal	<1	mg/L	
072013014427	PET Blue body	decolour test (65% ethanol)	Negative	---	
072013014427	PET Blue body	decolor test (soak)	Negative	---	
072013014427	PET Blue body	decolor test (buffet oil)	Negative	---	
072013014427	PET Blue body	Antimony (sb)	<0.010	µg/mL	
072013014428	PE Blue lid	evaporation residue (4% acetic acid)	<5.0	mg/L	GB/T 5009.60-2003 GB/T 5009.156-2003
072013014428	PE Blue lid	evaporation residue (65% ethanol)	<5.0	mg/L	
072013014428	PE Blue lid	evaporation residue (n-hexane)	5.2	mg/L	
072013014428	PE Blue lid	Potassium permanganate consumption	0.874	mg/L	
072013014428	PE Blue lid	Heavy metal	<1	mg/L	
072013014428	PE Blue lid	Decolor test (buffet oil)	Negative	---	
072013014428	PE Blue lid	Decolor test (soak)	Negative	---	
072013014428	PE Blue lid	decolour test (65% ethanol)	Negative	---	

TO BE CONTINUED

TEST RESULT

072013014429	PE White Nozzle	evaporation residue (4% acetic acid)	<5.0	mg/L	GB/T 5009.60-2003 GB/T 5009.156-2003
072013014429	PE White Nozzle	evaporation residue (65% ethanol)	<5.0	mg/L	
072013014429	PE White Nozzle	evaporation residue (n-hexane)	49.8	mg/L	
072013014429	PE White Nozzle	Potassium permanganate consumption	0.874	mg/L	
072013014429	PE White Nozzle	Heavy metal	<1	mg/L	
072013014429	PE White Nozzle	Decolor test (buffet oil)	Negative	---	
072013014429	PE White Nozzle	Decolor test (soak)	Negative	---	
072013014429	PE White Nozzle	decolour test (65% ethanol)	Negative	---	

*** END OF THE REPORT ***